

EUROPA EU				ESTADOS UNIDOS	
N° de Material	Simbólico E	Denominación DIN	Norma EN	Equivalente ASTM	Grado
1.1938	S235JR	St 37-2	EN 10025-2	A 283	B - C
1.1944	S275JR	St 44-2	EN 10025-2	A 36	-
1.1945	S355JR	-	EN 10025-2	A 283	D
1.0570	S355J2	St 52-3 N	EN 10025-2	A 573	70
1.0425	P265GH	H II	EN 10028-2	A 285	C
1.0481	P295GH	17 Mn4	EN 10028-2	A 515	70
1.0487 / 88	P275NH / NL2	TStE 285	EN 10028-3	A516	60
1.0473	P355GH	19 Mn 6	EN 10028-2	A 516	70
1.0566	P355NL1	T StE 355	EN 10028-3	A 516	70
1.5415	16 Mo3	15 Mo 3	EN 10028-2	A 204	A + B + C + D
1.7335	13CrMo4-5	13 CrMo 4-5	EN 10028-2	A 387	11 Cl. 2
1.7336	13CrMoSi5-5	13CrMoSi 5-5	EN 10028-2	A 387	12 Cl. 2
1.7380	10 CrMo 9-10	10 CrMo 9-10	EN 10028-2	A 387	22 Cl. 2
1.8915	P460NL1	T StE 460	EN 10028-3	A 572	65
1.7131	16 MnCr 5	16 MnCr 5	EN 10084	A 519	5120
1.7147	20 MnCr 5	20 MnCr 5	EN 10084	A 519	5120
1.7218	25 CrMo 4	25 CrMo 4	EN 10083	A 519	4130
1.7225	42 CrMo 4	42 CrMo 4	EN 10083-3	A 519	4140